



**MIZU
TANI
PH**

MIZUKEI BOUJINTEX SHOP CLEAR

**1K WATER-BASED POLYURETHANE
STAIN RESISTANT**

**WWW.MIZUTANIPPI.COM
INFO@MIZUTANIPPI.COM
632.809.1316**

**MIZUTANI PAINT PHILIPPINES INC.
M.GREENFIELD INDUSTRIAL COMP.
KM 14, MERVILLE ACCESS ROAD,
PARANAQUE CITY, PHILIPPINES, 1700**

BOUJINTEX SHOP CLEAR

DESCRIPTION

MIZUKEI BOUJINTEX SHOP CLEAR is a one-component, water based, interior acrylic floor paint that is formulated with a special urethane resin.

MIZUKEI BOUJINTEX SHOP CLEAR is durable and excellent in scratch resistance. Ideal for clear finish of mortar/concrete and topcoat for protective water-based acrylic paints.

DETAILS

Type: Polyurethane, Water-based, 1K
 Use: Interior Floor
 Finish: Gloss
 Surface: Concrete / Mortar
 Method: Brush / Roller
 Painting Interval (23°C): 2 hrs.
 Walk-able: 6 hrs.
 Fully Cured: 2 days
 Performance: 1 - 4 yrs.
 Coverage: 113 m² / 15 kg can / coat
 Coverage: 30 m² / 4 kg can / coat

FEATURES

1. High Gloss Finish
2. Scratch Resistant
3. Stain Resistant
4. Hard Film Type
5. Dust Proof
6. Water based – Eco-friendly, releases low odor, prevents danger of fire or solvent intoxication.
7. One component – economical, easy application by brush or roller.

USE

Ideal for clear finish of mortar/concrete and topcoat for protective water-based acrylic paints.

MATERIALS

TOPCOAT: BOUJINTEX SHOP CLEAR (15 kg can)

PRIMER: MIZUKEI BOUJINTEX EPOXY SEALER II 14kg set (base 7kg / hardener 7kg)

METHOD: GLOSS FINISH

SHOP CLEAR GLOSS ON MORTAR / CONCRETE	MATERIAL	MIX RATIO	METHOD	FREQUENCY	AMOUNT	COVERAGE	POT LIFE	INTERVAL
1. SURFACE PREPERATION	Remove any excessive laitance using a polisher or sanding machine (linax) until the base substrate is roughened sufficiently for adhesion. Remove any barrier such as existing sealer, curing material, grease, oil, and dirt. Treat cracks, holes, or any other surface unevenness with epoxy putty after primer.							
2. PRIMER	Mizukei Btx Epoxy Sealer II (7kg base, 7kg hardener)	-	Brush/ Roller	1 (2)	0.12 to 0.16 kg/m ² /coat	88 to 116 m ² /set (44 to 58 m ² /set)	60 min.	4 to 48 hrs.
3. TOPCOAT	Mizukei Boujintex Shop Clear (15kg)	1.5 to 3.0 kg	Brush/ Roller	2	0.12 to 0.15 kg/m ² /coat	50 to 63 m ² /can	-	2 hrs.